

Product Data Sheet

Product Code: MTPCSB

Product Description: 80/20% polyester cotton 4:1satin Work wear

TEST	SPECIFICATION	TEST METHOD
Base Fabric	80/20% poly cotton wp 4:1satin	ISO 1833
Construction	128x44	ISO 7211/2
Coating	N/A	
Finish	Pure Finish	
Fabric Weight	280 g/m2	ISO 3801
Coated Weight	N/A	ISO 3801
Total Weight	N/A	ISO 3801
Useable Width	160cms	EN 1773
Chromaticity to EN2041	YES	EN20471
Spray Rating	N/A	ISO 4920
Tensile Strength Warp (N)	>400N	ISO 13934-1
Tensile Strength Weft (N)	>400N	ISO 13934-1
Tear Strength Warp (N)	>35N	ISO 4674
Tear Strength Weft (N)	>35N	ISO 4674
Colour Fastness to light	4	ISO 105
Colour Fastness to Water	4	ISO 105 E01
Colour Fastness perspiration acid	4	ISO 105 E04
Colour Fastness perspiration alkaline	4	ISO 105 E04
Colour Fastness to Washing 40c	4	ISO 105 C06
Fastness to Rubbing Wet Dry	4	ISO 105 x12
Dimensional Stability	2%	ISO 6330
Pilling Resistance	N/A	ISO 12045.1.2000
Abrasion Resistance	100000	ISO 12947-2-2000
Water Vapour Resistance Ret	N/A	ISO 11092
Resistance to Water Penetration	N/A	ISO 20811

DISCLAIMER The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.

Product Code:MTPCSB

WASHING INSTRUCTION



- 1.Hot machine wash 60C
- 2.No Bleach or colour additives
- 3.Tumble dry normal medium heat
- 4.Regular ironing steam or dry

ADDRESS: TEXCHANNEL IMP. & EXP. CO., LTD.
ROOM 2302A,BANK CENTER ,NO.189 XIAHE ROAD,XIAMEN 361003 P.R. CHINA

SIGNED:

陈美平



DISCLAIMER: The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.