

Product Data Sheet

Product Code: MTCNTAFR

Product Description: 88% Cotton 12% Nylon Twill 2:1 Permanent Fire
retardant End Use work Wear

TEST	SPECIFICATION	TEST METHOD
Base Fabric	Cotton 88%Nylon 12%	ISO 1833
Construction	16ne x 16ne 78x51	ISO 7211/2
Coating	N/A	
Finish	Flame	
Fabric Weight	N/A	ISO 3801
Coated Weight	N/A	ISO 3801
Total Weight	250g/m2+/-3%	ISO 3801
Useable Width	148cms	EN 1773
Chromaticity to EN2041	N/A	EN20471
Spray Rating	N/A	ISO 4920
Tensile Strength Warp (N)	700N	ISO 13934-1
Tensile Strength Weft (N)	700N	ISO 13934-1
Tear Strength Warp (N)	40N	ISO 4674
Tear Strength Weft (N)	40N	ISO 4674
Colour Fastness to light	4-5	ISO 105
Colour Fastness to Water	4	ISO 105 E01
Colour Fastness perspiration acid	4	ISO 105 E04
Colour Fastness perspiration alkaline	4	ISO 105 E04
Colour Fastness to Washing 40c	4	ISO 105 C06
Fastness to Rubbing Wet Dry	4	ISO 105 x12
Dimensional Stability	2-3%	ISO 6330
Pilling Resistance	3	ISO 12045.1.2000
Abrasion Resistance	60000	ISO 12947-2-2000
Water Vapour Resistance Ret	N/A	ISO 11092
Resistance to Water Penetration	N/A	ISO 20811
Flame Resistance		ATM D6413
Char length inches (warp fill)	<4.0x <4.0	
After flame seconds (warp fill)	0.0x0.0	

DISCLAIMER The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.

Product Code:MTCNTAFR

WASHING INSTRUCTION



- 1.Hot machine wash 70C
- 2.No Bleach or colour additives
- 3.Tumble dry gentle cycle low heat
- 4.Cool Iron no steam

ADDRESS: TEXCHANNEL IMP. & EXP. CO., LTD.
ROOM 2302A,BANK CENTER ,NO.189 XIAHE ROAD,XIAMEN 361003 P.R. CHINA

SIGNED:

陈永平



DISCLAIMER: The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.