

## Product Data Sheet

**Product Code: MTCPTA**

Product Description: 60% Cotton 40 % Polyester 3/1 warp Twill

TEST	End Use Coverall SPECIFICATION	TEST METHOD
Base Fabric	60% 40% Cotton Polyester	ISO 1833
Construction	150f48 x 10s cotton 124x58	ISO 7211/2
Coating	N/A	
Finish	N/A	
Fabric Weight	N/A	ISO 3801
Coated Weight	N/A	ISO 3801
Total Weight	130g/m2	ISO 3801
Useable Width	152cms	EN 1773
Chromaticity to EN2041	YES	EN20471
Spray Rating	5	ISO 4920
Tensile Strength Warp (N)1000N		ISO 13934-1
Tensile Strength Weft (N)700N		ISO 13934-1
Tear Strength Warp (N)50N		ISO 4674
Tear Strength Weft (N)50N		ISO 4674
Colour Fastness to light	4	ISO 105
Colour Fastness to Water	4	ISO 105 E01
Colour Fastness perspiration acid	4	ISO 105 E04
Colour Fastness perspiration alkaline	4	ISO 105 E04
Colour Fastness to Washing 70c 4		ISO 105 C06
Fastness to Rubbing Wet Dry	4	ISO 105 x12
Dimensional Stability	2-3%	ISO 6330
Pilling Resistance	4	ISO 12045.1.2000
Abrasion Resistance	60000	ISO 12947-2-2000
Water Vapour Resistance Ret	N/A	ISO 11092
Resistance to Water Penetration	N/A	ISO 20811

**DISCLAIMER**The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.

**Product Code:MTCPTA**

**WASHING INSTRUCTION**



- 1.Hot machine wash 60C
- 2.No Bleach or colour additives
- 3.Tumble dry gentle cycle low heat
- 4.Medium Iron with without steam

**ADDRESS:** TEXCHANNEL IMP. & EXP. CO., LTD.  
ROOM 2302A,BANK CENTER ,NO.189 XIAHE ROAD,XIAMEN 361003 P.R. CHINA

**SIGNED:**

陈美平



**DISCLAIMER:** The information contained in the product Data Sheet is based on results obtained on the sample assessed at the time in accordance with the method provided. The values are a guide to purchasers of the Fabric to evaluate the Fabric and determine its suitability for their products intended end use.